

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11) Publication number:

**0 487 000 B1**

(12)

## EUROPEAN PATENT SPECIFICATION

(49) Date of publication of patent specification: **23.08.95** (51) Int. Cl.<sup>6</sup>: **A61K 7/48**

(21) Application number: **91119655.8**

(22) Date of filing: **18.11.91**

(54) **Cosmetics containing enzymatically debranched starch.**

(30) Priority: **19.11.90 US 615725**

(43) Date of publication of application:  
**27.05.92 Bulletin 92/22**

(45) Publication of the grant of the patent:  
**23.08.95 Bulletin 95/34**

(84) Designated Contracting States:  
**AT BE CH DE DK FR GB LI LU NL SE**

(56) References cited:  
**EP-A- 0 372 184**  
**GB-A- 1 143 219**  
**US-A- 3 957 969**  
**US-A- 4 970 220**

(73) Proprietor: **National Starch and Chemical Investment Holding Corporation**  
**501 Silverside Road**  
**Wilmington, Delaware 19809 (US)**

(72) Inventor: **Rouse, William**  
**1639 Bunts Road**  
**Lakewood,**  
**Ohio 44107 (US)**  
Inventor: **Valles, Maria**  
**39 Kilmer Drive**  
**Colonia,**  
**New Jersey 07067 (US)**  
Inventor: **Martino, Gary**  
**52 Bradford Lane**  
**Plainsboro,**  
**New Jersey 08536 (US)**  
Inventor: **Chiu, Chung-Wai**  
**305 Woods End Road**  
**Westfield,**  
**New Jersey 08840 (US)**

(74) Representative: **Hagemann, Heinrich, Dr. rer. nat., Dipl.-Chem. et al**  
**Patentanwälte**  
**Hagemann & Kehl**  
**Postfach 86 03 29**  
**D-81630 München (DE)**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

**EP 0 487 000 B1**

## Description

This invention relates to cosmetics comprising enzymatically debranched starch, and in particular, cosmetics which are stable, smooth-textured, water-in-oil emulsions.

Humectant and tactile properties such as a soft feel on the skin and lips, and a smooth, easily spreadable texture are highly desirable in cosmetics. In stick products, such as lipstick, lip balm, stick deodorants and other similar cosmetics, a formulation providing a stable, rigid form, in addition to humectant and tactile properties, is highly desirable. These tactile properties are provided in conventional cosmetic compositions by hydrophobic ingredients such as waxes, oils and fats.

Improved humectant properties are provided by adding hydrophilic ingredients to the composition and forming a stable water-in-oil emulsion. The emulsion compositions known in the art suffer from several drawbacks including lack of emulsion stability, particularly in stick compositions and high ingredient costs (e.g., hyaluronic acid costs), particularly in cream, lotion and beauty soap compositions.

It has been discovered that cosmetic compositions containing certain enzymatically debranched starches are characterized by stability and excellent humectant and tactile properties. It has been discovered that oil-free lotions may be formulated with the enzymatically debranched starches. The enzymatically debranched starches have been characterized as having unique gelling, lubricating and film-forming properties in aqueous dispersion US-A- 4,971,723 and US-A- 4,886,678; and US-A- 4,937,091. US-A- 3,957,969, discloses the use of various polyhydroxyl compounds, including starch, in cosmetic stick formulations. It now has been discovered that only enzymatically debranched starches, and not starches in general, are useful in cosmetic stick formulations.

Starch is a polysaccharide typically comprising a mixture of about 20-25% amylose and about 75-80% amylopectin which is organized into compact granular structures. Amylose is a linear polymer of D-anhydroglucose units which are linked by alpha-1,4-D-glucosidic bonds. Amylopectin is a large branched polymer of amylose chains linked by alpha-1,6-D-glucosidic bonds in a tree-like structure. Depending upon the variety of plant from which the starch is obtained, amylose ordinarily contains between 250 and 12,500 D-anhydroglucose units and amylopectin contains between 400,000 and 3,125,000 D-anhydroglucose units. As used herein, "short chain amylose" refers to linear polymers containing from about 15 to 65 anhydroglucose units linked by alpha-1,4-D-glucosidic bonds.

Enzymes, or mixtures of enzymes which saccharify and debranch starch, have been used in starch conversion processes for the commercial production of low molecular weight oligosaccharides and sugars, such as dextrose (glucose). Starch conversion is the degradation of starch to lower molecular weight components by treatment with acid, oxidizing agents, heat, alkali or alpha-amylase enzymes. Enzymatic conversion of starch typically involves preferential hydrolysis of the alpha-1,4-D-glucosidic bonds, and only limited, if any, hydrolysis of the alpha-1,6-D-glucosidic bonds.

Glucoamylase rapidly hydrolyzes alpha-1,4-D-glucosidic bonds and slowly hydrolyzes alpha-1,6-D-glucosidic bonds, releasing glucose. In contrast, a debranching enzyme, such as pullulanase or isoamylase, rapidly hydrolyzes only the alpha-1,6-D-glucosidic bonds, releasing short chain amylose.

Debranching enzymes (enzymes which release short chain amylose from starch) have been proposed for use in conjunction with glucoamylase and alpha-amylase to improve the efficiency of production of high dextrose syrups; in low calorie alcoholic beverage production to improve fermentability of branched starch fragments; in production of maltose from starch in conjunction with beta-amylase; in low DE maltodextrin (30-55 glucose units) production to induce proteins to aggregate in aqueous emulsions; and in enzymatic conversion of starch into a soluble syrup having a high quantity of disaccharides and trisaccharides. These debranching enzyme applications are directed to problems arising from the presence of branched starch or dextrin fragments following starch conversion processes. In each application, the debranching enzyme is employed in the complete conversion of starch to a variety of low molecular weight fragments such as sugars or maltodextrins. The thickening, adhesion and gelling characteristics of starch are lost.

The use of debranching enzymes to fully debranch starch, with hydrolysis of substantially all alpha-1,6-D-glucosidic bonds, so as to obtain pure, or amylopectin-free, low molecular weight amylose is taught in US-A-3,730,840; US-A- 3,881,991; and US-A- 3,879,212. The object of these patents is to produce pure short chain amylose. The presence of any residual amylopectin is taught to be objectionable. No disclosure is made of any lubricating or humectant properties or utilities within the field of cosmetics formulation.

GB-A-1 143 219 describes an acid hydrolysed starch which is subjected to mechanical disintegration. At levels up to 5% solids, a stable dispersion may be formed from the acid hydrolyzed starch. At levels up to 10% solids, a stable gel may be formed from the starch. This patent specification concerns high amylose starch materials, i.e. at least 50% amylose. The starch is first subjected to a chemical process and then to a physical process to provide stability in dispersion. The amylose referred to in this specification is native

amylose which is a linear polymer of about 250 to 12,500 D-anhydroglucose units.

Thus, the background of enzyme-related starch technology does not suggest that starches useful as ingredients in cosmetic compositions may be prepared by employing debranching enzymes to debranch the amylopectin component of starch, yielding short chain amylose, and, optionally, partially debranched amylopectin, native amylose, or amylopectin, with or without substantial conversion of the starch. These starches and the enzymatic process offer significant advantages over other products and processes in cosmetics where "natural" and "hypo-allergenic" claims frequently appear in product marketing programs.

This invention provides enzymatically debranched starches, comprising 15 to 100%, by weight, linear polymers containing from about 15 to 65 anhydroglucose units linked by  $\alpha$ -1,4-D-glucosidic bonds (short chain amylose), for use in cosmetics. Aqueous dispersions of these debranched starches are characterized by a variety of fat-like textures ranging from oily to creamy to waxy which are useful in cosmetics. These starches may be selected to provide high strength starch gels or thermoreversible starch gels in aqueous dispersions. A thermally reversible starch gel is one which melts upon heating and reforms upon cooling. Gels prepared from unmodified starches are not thermally reversible.

This invention also provides water-in-oil emulsion and oil-free cosmetic compositions, and cosmetic stick compositions, formulated with enzymatically debranched starches.

Emulsion-containing cosmetic compositions, wherein the emulsion comprises a 15 to 40% solids, by weight, aqueous dispersion of an enzymatically degraded starch, which starch has been debranched by treatment with an  $\alpha$ -1,6-D-glucanohydrolase to yield up to 100%, by weight, short chain amylose, are provided herein.

Also provided are cosmetic stick compositions, comprising 1 to 16% starch which has been enzymatically debranched to yield from 15 to 100%, by weight, short chain amylose; 2 to 35% water; 35 to 90% hydrophobic base, selected from oil, wax and fat; and 5 to 20% emulsifier(s), with the balance of the compositions comprising one or more adjuncts selected from dye(s), preservative(s), fragrance(s), flavor(s), sunscreen agent(s), opacifier(s), and filler(s).

Also provided is a method for formulating a cosmetic stick composition which comprises:

- a) dispersing an enzymatically debranched starch which has been debranched by  $\alpha$ -1,6-D-glucanohydrolase in an aqueous solvent at 15 to 40%, by weight, solids;
- b) heating the dispersed starch to 70-100°C;
- c) adding to the dispersed starch a hydrophobic phase at 70-100°C, which hydrophobic phase comprises at least one hydrophobic ingredient and at least one emulsifier;
- d) blending the dispersed starch into the hydrophobic phase to provide an emulsion; and
- e) forming the cosmetic stick from the emulsion; whereby the emulsion is uniform and the cosmetic stick composition is stable.

The starches which are enzymatically debranched for use herein may be derived from any source, including corn, potato, sweet potato, wheat, rice, sago, tapioca, waxy maize, sorghum, and the like. Also included are the conversion products derived from any of the above starches, including fluidity or thin-boiling starches prepared by oxidation,  $\alpha$ -amylase conversion, mild acid hydrolysis or heat dextrinization. Crosslinked or derivatized starches, such as ethers and esters, and other modified starches also may be employed.

The starch will preferably be a gelatinized starch (a precooked, cold-water-swelling starch) and also may be a fluidity starch converted by mild acid degradation, heat dextrinization, or any one of several methods that are well known in the art. See, e.g., M. W. Rutenberg, "Starch and Its Modifications" P. 22-36, in Handbook of Water-Soluble Gums and Resins, R.L. Davidson, editor, McGraw Hill, Inc., New York, New York, 1980. If desired, the starch may be converted by treatment with an  $\alpha$ -amylase to produce a fluidity starch in the manner disclosed in US-A- 4,726,957. A combination of one or more of these conversion techniques may be used. The conversion is typically carried out before derivatization or crosslinking, but may be carried out before or after the enzymatic treatment. Where a high viscosity debranched starch is desired, it is not desirable to convert the starch.

Where a low viscosity starch is desirable, a starch, such as waxy maize, which has been converted to a Water Fluidity (WF) of up to about 60 is preferred. Water Fluidity is an empirical measure of viscosity on a scale of 0-90, wherein fluidity is the reciprocal of viscosity.

For other products, derivatization to any degree of substitution or level of conversion that results in the desired viscosity and functional characteristics may be employed prior to, or following, enzymatic debranching. For example, the debranched starch may be employed as an emulsifying agent in cosmetics (e.g., the moisturizer sunscreen formulation herein) and an emulsifying starch, such as octenylsuccinate derivative (OSA starch), is preferred. The starch is treated with octenylsuccinic acid anhydride to form a starch ester derivative containing from 0.25 to 3.0%, by weight, of octenylsuccinate.

In a preferred embodiment, the next step after preparing the starch derivative is to heat an aqueous dispersion of the derivatized starch to gelatinize the derivatized starch. The gelatinization process disrupts, in whole or in part, the associative bonding of the starch molecule within the raw starch granule, thereby making the molecule more accessible to the enzyme and permitting the enzyme to more easily and uniformly debranch the starch molecules. After a slurry of the starch has been gelatinized, the solids, temperature and pH of the dispersion are adjusted to provide optimum enzyme activity.

The optimum parameters for enzyme activity will vary depending upon factors including enzyme concentration, substrate concentration, pH, temperature, the presence or absence of inhibitors and other factors. Depending on the type of enzyme, or its source, various parameters may require adjustment to achieve optimum debranching rate. In general, enzymatic debranching is carried out at the highest feasible solids content to facilitate subsequent drying of the starch while maintaining optimum debranching rates. For example, for the pullulanase used herein to produce a starch suitable for use in cosmetics, a precooked starch dispersion ranging up to 28% solids is preferred.

The practitioner will recognize that a higher solids starch system (e.g., above 50% solids) may be employed if the starch is gelatinized by a process which produces adequate mixing to uniformly blend the enzyme and the starch at higher solids. The practitioner also will recognize that the temperature, treatment time and other parameters of the enzymatic debranching process must be adjusted to the higher solids content. Processes which employ higher solids starch dispersions are intended to fall within the scope of this invention and may be used to prepare the short chain amylose.

Although the preparation of short chain amylose herein employs pullulanase (E.C. 3.2. 1.41; pullulan 6-glucanohydrolase) as the enzyme, other endo- $\alpha$ -1,6-glucanohydrolases, such as isoamylase (E.C. 3.2. 1.68), or any other endo-enzyme which exhibits selectivity in cleaving the 1,6-linkages of the starch molecule, leaving the 1,4-linkages substantially intact and releasing short chain amylose, may be used.

In a preferred embodiment, the enzyme used is a heat stable pullulanase obtained from a novel species of *Bacillus*. This pullulanase will catalyze the hydrolysis of the  $\alpha$ -1,6 linkages in pullulan and amylopectin, provided that there are at least two glucose units in the side chain. Pullulanase is a linear polymer consisting essentially of D-glucopyranosyl triose units joined by  $\alpha$ -1,6 linkages.

Optimum concentrations of enzyme and substrate are governed by the level of enzyme activity which will vary depending upon the enzyme source, the enzyme supplier and the concentration of the enzyme provided in commercially available batches. Although the process of this invention makes use of an enzyme in solution, processes utilizing an enzyme immobilized on a solid support are intended to fall within the scope of this invention.

The reaction may proceed in the presence of buffers to ensure that the pH will be at the optimum level throughout the degradation. Buffers such as acetates, citrates, or the salts of other weak acids are acceptable. Other agents may be used to optimize enzyme activity. The reaction may be carried out in a pH range from about 3.0 to 7.5, with the preferred range being between 4.5 and 5.5, and the optimum being 5.0 when the temperature is 60°C and the enzyme is the *Bacillus* pullulanase.

The aqueous starch dispersion should be held during the enzymatic debranching at a temperature of about 25-100°C, the preferred range being 55-65°C and the optimum being 60°C at pH 5.0 for the *Bacillus* pullulanase. However, if shorter treatment times are desired, a temperature range from 60-65°C or a higher enzyme concentration may be used. Alternatively, a higher temperature may be employed if a thermally stable debranching enzyme is selected for use herein. As with other parameters of the enzyme reaction, the preferred and optimum temperature ranges will vary with changes in other parameters such as substrate concentration, pH and other factors affecting enzyme activity, and can be determined by the practitioner.

The enzymatic treatment is permitted to continue until the desired amount of short chain amylose is produced. The progress of the enzymatic treatment may be measured by various methods. If all critical parameters have been established for achieving a particular starch composition, then the treatment may be allowed to proceed to a predetermined relative end point in time. The end point may be determined by change in viscosity of the starch dispersion, by gel permeation chromatography, by reducing group content, iodine reaction or by any other method known in the art for measuring the degree of enzymatic debranching of the starch molecule.

In a preferred embodiment, the debranching, end point is measured by determining the viscosity of a starch dispersion at 22°C (72°F) using the funnel viscosity method set forth in Example 1, below. The funnel viscosity method is a rapid, simple method for determining viscosity, in which the amount of time needed for a standard quantity of starch slurry to flow through a standard size funnel is recorded.

In a second preferred embodiment, the degree of starch debranching is measured by gel permeation chromatography. After separating the starch into its different molecular weight fractions, the percentage of

short chain amylose is determined by calculating the percentage, by weight, of the low molecular weight fraction of the partially debranched starch. It will be understood by the practitioner that these percentages are approximately equal to the amount of short chain amylose which has been liberated from the amylopectin by the debranching enzyme. Experimental error in gel permeation chromatography (e.g., due to contamination by the enzyme, or by sugars or dextrans introduced with the starch, the enzyme solution, the buffer or other process components) may result in a percent low molecular weight fraction which may range up to 5% more or less than the percent short chain amylose of the starch sample.

The degree of starch debranching needed for a particular application depends on the type of starch utilized, the presence and nature of any substituent groups and the degree, if any, of conversion. The practitioner will be able to select a suitable starch and determine the necessary debranching for any particular cosmetic with a minimum of experimentation.

While any amylopectin-containing starch may be employed, the effects of enzymatic debranching will be more dramatic as the amylopectin content of the starch increases. Thus, although all commercially available starches may be employed herein, waxy maize which contains about 100% amylopectin is preferred.

In a preferred embodiment, waxy maize starch, or some other waxy starch (e.g., waxy rice or barley starch), is debranched, yielding sufficient short chain amylose to create a mixture comprising from 15 to 100% short chain amylose, and preferably, from 35 to 100% short chain amylose. This degree of debranching of waxy starches is preferred for creating a fat-like, lubricating texture in an aqueous starch dispersion. Fat-like properties are generally enhanced as the percent short chain amylose increases. Converted, debranched waxy starches (e.g., 50 WF acid-converted waxy maize or waxy rice) also are preferred for preparing a thermally reversible gel and providing lubricating qualities in an aqueous starch dispersion.

For preparing high strength starch gels, partially debranched corn starch, comprising 10 to 45% short chain amylose, and preferably 15 to 40% short chain amylose, is preferred.

After the desired degree of starch debranching has been reached, the enzyme may be deactivated. Pullulanase is rapidly deactivated at temperatures above about 70°C, therefore, the reaction may be conveniently terminated by increasing the temperature of the starch dispersion to at least 75°C for about 15 minutes.

If use in cosmetics requires purification of the debranched starch, the reaction impurities and by-products may be removed by dialysis, filtration, ion exchange processes, centrifugation or any other method known in the art for isolating and recovering the starch.

If a dried starch is desired for cosmetics applications, the starch may be dehydrated by any method known in the art.

It is to be understood that the invention includes starch blends which contain 15 to 100% short chain amylose. Thus, this invention includes blends of debranched starch and other components, such as chemically modified starches and other polymers, and includes multi-step processes in which an enzyme is employed in one step to debranch starch. For example, this invention includes multi-step processes and starch blends wherein the starch is converted, derivatized, crosslinked or otherwise modified in addition to being subjected to enzymatic debranching, or being blended with short chain amylose.

The debranched starch may be employed alone, or as a starch blend, in any cosmetic formulation. The nature of the cosmetic formulation will direct the selection of an appropriate debranched starch from those disclosed herein. In a preferred embodiment, a cosmetic stick formulation comprises 1 to 16% starch which has been enzymatically debranched to yield from 15 to 100%, by weight, short chain amylose; 2 to 35% water; 35 to 90% hydrophobic base, selected from the group consisting of oil, wax and fat; 5 to 20% emulsifier(s); and one or more adjuncts selected from dye(s), preservative(s), fragrance(s), flavor(s), sunscreen agent(s), opacifier(s), and filler(s).

In another preferred embodiment enzymatically debranched starch is employed in a cosmetic composition disclosed in US-A- 4,970,220, which is hereby incorporated by reference.

The following examples will more fully illustrate the embodiments of this invention. In these examples, all parts and percentages are given by dry weight basis and all temperature are in degrees Celsius unless otherwise noted.

#### EXAMPLE 1

This example illustrates the preparation of representative partially debranched starches by the process of this invention.

The starches were converted, derivatized or crosslinked, where applicable, prior to gelatinization and treatment with pullulanase. To convert the starch, a slurry of 100 parts of starch in 150 parts of water was heated to 52°C, the indicated amount of hydrochloric acid (1.75%) was added, and the mixture was stirred for 16 hours at 52°C. The hydrolysis was stopped by neutralizing the mixture with alkali (a solution of 3% sodium hydroxide) to a pH of 5.5. The converted starch was recovered by filtration, washed and dried.

#### **STARCH DERIVATIZATION**

To prepare the octenylsuccinate derivative, 100 parts of starch was slurried in 150 parts water, the pH was adjusted to 7.5 with sodium hydroxide, and the indicated amount of octenylsuccinic anhydride was added slowly while the pH was maintained at 7.5 with alkali. The reaction was complete when no further addition of alkali was necessary. The pH was adjusted to between 4.0 and 6.5 and the resulting derivatives were recovered by filtration, washed and dried.

To prepare the acetate derivative, 100 parts of the starch was slurried in 150 parts by water, adjusting the pH to 8.3 with 3% sodium hydroxide solution, and slowly adding the indicated amount of acetic anhydride while maintaining the pH at 8.3 with the above alkali. The reaction was complete when no further addition of alkali was necessary. The pH was adjusted to between 4.0 and 6.5 and the resulting derivative was recovered as above.

The crosslinked starch was prepared by slurring 100 parts of starch in 150 parts water, adding 0.8 parts sodium hydroxide, 1.0 parts sodium chloride, and then adding the indicated amount of phosphorus oxychloride. The slurry was agitated for 3 hours at room temperature. When the reaction was completed, the pH was adjusted to 5.5 with acid. The starch was recovered by filtration, washed and dried.

#### **STARCH DEBRANCHING**

An aqueous slurry (20-30% solids) was prepared employing the desired starch. The aqueous starch slurry was jet-cooked at approximately 300°F (149°C) to gelatinize the starch. The cooked starch dispersion was placed in a constant temperature bath at 58-60°C with constant stirring. The pH was adjusted to 5 with 3% hydrochloric acid.

Depending on the type of starch used and its amylopectin content, between 0.5 and 10.0 ml of pullulanase per 100 g of starch were added to the cooked starch dispersion. The pullulanase (E.C. 3.2.1.41, pullulan 6-glucano-hydrolase) which was used is produced by a novel species of *Bacillus*. This enzyme (Promozyme®) was obtained from Novo Industri A/S of Denmark. The enzymatic activity of Promozyme in a 1.25 g/ml solution is standardized at 200 PUN/ml of solution. One PUN (Pullulanase Unit Novo) is the amount of enzyme which, under standard conditions, hydrolyzes pullulan, liberating reducing carbohydrate with a reducing power equivalent to 1 micro-mol glucose per minute. The procedure for determining PUN is available from Novo Industri A/S.

Thus, in the starch dispersion employing corn starch, 125 PUN of pullulanase per 100 g corn starch was added to the dispersion. For the waxy maize starch slurry (with higher amylopectin content), 750 PUN of pullulanase per 100 g waxy maize starch was added to the dispersion.

The amount of debranching was measured initially by the funnel viscosity test and subsequently by gel permeation chromatography.

#### **FUNNEL VISCOSITY MEASUREMENT**

To measure funnel viscosity at 19% solids, 38 g of the starch (anhydrous basis) was weighed into a tared 250 ml beaker (stainless steel) containing a thermometer and brought to 200 g total weight with distilled water. The sample was mixed to dissolve any lumps and heated or cooled to 72°F (22°C). A total of 100 ml of the cooked starch dispersion was measured into a graduated cylinder. It was then poured into a calibrated funnel while using a finger to close the orifice. A small amount was allowed to flow into the graduate to remove any trapped air, and the complete balance remaining in the graduate was poured back into the funnel. Using a timer, the time required for the 100 ml samples to flow through the apex of the funnel was recorded.

The funnel was a standard 58°, thick-wall, resistance glass funnel whose top diameter was about 9-10 cm with the inside diameter of the stem being about 0.381 cm. The funnel was calibrated so as to allow 100 ml of water to go through in 6 seconds using the above procedure.

**CORN STARCH (CAUSTIC) FUNNEL VISCOSITY**

Due to retrogradation of the starch which occurs when using corn starch, the funnel viscosity measurement was modified as follows for debranched corn starch:

- 5 1. the starch sample weight was reduced to 15 g (anhydrous basis);
2. sufficient hot (at least 90 °C) water was added to the starch to bring it to 150 g total weight;
3. 15 g of 25% w/v sodium hydroxide solution was added to the hot starch slurry; and
4. with stirring, the slurry was cooled to 22 °C (72 °F) and the measurement carried out as set forth above.

**GEL PERMEATION CHROMATOGRAPHY**

15 Starches were prepared for analysis by slurrying 5 mg of starch in 4 ml of dimethylsulfoxide ("DMSO") containing 0.03M sodium nitrate and heating the slurry to 80 °C for at least 30 minutes to dissolve the starch. Samples (200 µl) were injected into an ALC/GPC-150C Chromatograph (Waters Associates, Milford, Massachusetts) (equipped with a Nelson 3000 Series Chromatography Data System and two PL gel mixed 10 µm columns (obtained from Polymer Laboratory, Amherst, Massachusetts), employing DMSO containing 0.03 M sodium nitrate as the mobile phase) and eluted at a rate of 1 ml/min. The columns were calibrated using dextran standards (with molecular weights of 2,000; 20,000; 80,000; 500,000; and 2,000,000 obtained from Pharmacia Fine Chemicals, Piscataway, New Jersey). The percentage short chain amylose was calculated from the relative area of the peak obtained within the molecular weight range from 500 to 20,000.

**PREPARATION OF DEBRANCHED OSA WAXY MAIZE STARCHES**

25 Employing the process set forth above, an OSA starch derivative was prepared by reacting 4,000 g of waxy maize starch with 1% octenylsuccinic anhydride. The starch was then jet cooked at pH 5.0 yield a 23% starch dispersion. Pullulanase (80 ml) was added to the dispersion at 58 °C with agitation. After 24, hours, the funnel viscosity was 35 seconds at 19% solids and 22 °C (72 °F).

30 The debranching was continued by adding an additional 80 mls of pullulanase at 58 °C and agitating the dispersion for an additional 3 hours. The pullulanase was deactivated by heating the dispersion to about 80 °C. The funnel viscosity was 12 seconds at 19% solids and 22 °C (72 °F). The starch dispersion was spray dried at an inlet temperature of 200-210 °C and an outlet temperature of 80-90 °C. The spray-dried starch was screened through #40 mesh screen.

35 A second sample of OSA waxy maize starch (4,000 g) was prepared and debranched in the same manner as the first sample, except that 20 ml of pullulanase was employed in a single addition. Debranching continued for two hours at which time the funnel viscosity was 50 seconds at 10% solids and 220 °C (72 °F). This sample was spray-dried in the same manner as the first sample.

**EXAMPLE 2**

40 This example illustrates the preparation of partially debranched starch employing the enzyme isoamylase (glycogen 6-glucano-hydrolase; E.C. 3.2.1.68).

45 A cooked, 24% solids, aqueous dispersion of waxy maize starch (2,500g) was treated with 5,000 units of a *Pseudomonas amyloclavata* isoamylase (obtained from Sigma Chemical Company, St. Louis, Missouri). One unit of this isoamylase causes an increase in absorbance ( $A_{610}$ ) of 0.1 in 1 hour using rice starch as a substrate.

50 The starch dispersion was heated to 45 °C at pH 4.0, the enzyme was added and the mixture was stirred for 26 hours. A portion of the mixture was removed, heated to 80 °C to deactivate the enzyme, and spray-dried and screened as in Example 1. The remaining portion of the starch mixture was enzymatically treated for a total of 43 hours, at which time the enzyme was deactivated and the starch dried and screened as above.

The quantity of short chain amylose obtained from isoamylase hydrolysis was measured with gel permeation chromatography. The 26 hour sample contained 21.9% and the 43 hour sample contained 28.4% short chain amylose.

**EXAMPLE 3**

This example illustrates the relationships between treatment time, funnel viscosity (or Water Fluidity) and percentage short chain amylose of the starches of this invention.

The partial enzymatic debranching process of Example 1 was carried out on the starches listed in Table I.

The funnel viscosity and percent short chain amylose were measured by the methods as set forth above. Results are shown in Table I.

10

15

20

25

30

35

40

45

50

55



TABLE I

Starch	Treatment Time (h)	Funnel Viscosity (seconds)	% Solids	% Short Chain Amylose
Waxy-Maize Acid-converted to 50 WF				
1	0.5	110	19	13.5
2	1.0	22	19	26.3
3	20.0	20	19	27.1
4	20.0	18	19	31.8
5	25.0	14	19	35.1
6	44.0	12	19	48.0
Waxy-Maize				
1	0.25	110	19	22.1
2	1.0	52	19	23.8
3	20.0	20	19	32.6
4	20.0	16	19	40.0
5	24.0	12	19	45.6
6	45.0	12	19	51.9
Corn <sup>a</sup>				
1	1.0	97	10	14.5
2	3.0	37	10	21.9
3	5.0	30	10	26.5
4	7.0	27	10	24.9
5	24.0	18	10	33.3
6	48.0	12	10	47.5

<sup>a</sup>Caustic Funnel Viscosity.

The results show generally that as reaction time increases, the percent short chain amylose increases and the funnel viscosity decreases in a non-linear fashion. Thus, one or more of these measurements may be employed to measure the progress of the enzymatic debranching.

**EXAMPLE 4**

This example illustrates that the starch of this invention may be used to create lubricity and fat-like texture in an aqueous starch dispersion.

5 A waxy maize starch was partially debranched by the method of Example 1 to a funnel viscosity of 10-12 seconds at 22° C (72° F) 10% solids (about 50% short chain amylose).

Fat-like or lubricating properties of the starch were evaluated by dispersing 25g, anhydrous, of starch in 75g of distilled water. The dispersion was heated on a steam bath for 20 minutes, poured into a petri dish, refrigerated for one hour and subjectively evaluated. The partially debranched starch gel was spread on the  
10 palm of the hand and observed to have a lubricating, creamy touch. The gel was glossy and opaque.

Additional starches and starch blends were tested by the same method for fat-like properties in aqueous dispersions. These starches and starch blends and the test results are set forth in Table II, below. All samples exhibited fat-like properties, including blends of debranched waxy maize with tapioca maltodextrin or converted waxy maize or converted tapioca. The short chain amylose content of the debranched  
15 waxy maize starch ranged from 15 to 75%, by weight.

20

25

30

35

40

45

50

55

**TABLE II**  
**CHARACTERISTICS OF AQUEOUS DISPERSIONS**  
**OF DEBRANCHED STARCHES**

Debranched Starch Waxy Maize A <sup>a</sup>	Percent of Starch in Blend			Evaluation in Aqueous Dispersion (25% solids dispersion)
	Waxy Maize B <sup>b</sup>	C <sup>c</sup>	Converted Starch <sup>e</sup> 35WF 81WF Waxy Maize Tapioca	
100	--	--	--	glossy, opaque, creamy gel, spreadable
80	--	--	20	opaque, creamy, shortening
60	--	--	40	opaque, butter-like
20	--	--	80	opaque, oily
50	--	--	--	opaque, creamy, spreadable
75	--	--	25	opaque, creamy, spreadable
--	100	--	--	creamy, greasy, slight tack
--	50	--	50	creamy, buttery
--	--	100	--	creamy, spreadable gel
--	--	50	50	creamy, soft, greasy, spreadable gel

a. 50% short chain amylose  
b. 15% short chain amylose  
c. >75% short chain amylose  
d. an alpha-amylose converted, pregelatinized tapioca starch of the type disclosed in U.S. Pat. No. 4,510,166 to Lechin, et al.  
e. an acid-converted starch, converted by the method of Example 1.

US-11-

#### EXAMPLE 5

This example illustrated the preparation of a lipstick formulation using an aqueous dispersion of enzymatically debranched starch.

Lipsticks were prepared using the following formulation and procedure.

LIPSTICK FORMULATION	
INGREDIENT	PERCENT BY WEIGHT
<b>Phase A</b>	
Starch <sup>a</sup>	10.00
Distilled Water	30.00
<b>Phase B</b>	
Castor Oil	30.00
Candelilla Wax	15.00
Isopropyl Myristate	7.00
Sorbitan Oleate	1.00
Polysorbate 80	3.00
Dimethicone	3.00
<b>Phase C</b>	
Preservative <sup>b</sup>	1.00
	100.00

a. See Table III, below.

b. A mixture of propylene glycol, diazolidinyl urea, methylparaben and propylparaben.

Starches were prepared by the method of Example 1. The starch was slowly sifted into the water with agitation, heated to 80 °C and held for 30 minutes. The components of phase B were combined and heated to 80 °C with mixing. When both phases were completely dispersed, phase B was added to phase A with mixing and held at 80 °C for 30 minutes. This formulation was cooled to 40 °C with mixing and phase C was added.

Using this procedures, a series of lipstick samples were prepared from the debranched starches and control starches set forth in Table III, below. The samples were evaluated for the following tactile and visual properties:

Soft feel to the lips,  
Good spreading properties,  
Smooth texture, and  
Rigid stick form.

The lipsticks were subjected to elevated temperature studies to simulate accelerated shelf life.

Formulations were prepared and sealed in glass jars. Samples were placed in a closed oven at 49 °C (120 °F) and examined periodically. Results of the quality evaluations and the storage tests are set forth in Table III.

TABLE III

Starch Sample <sup>a</sup>	Lipstick Quality	Lipstick Stability
Control	phase separation	phase separation
Debranched converted waxy maize (58%) <sup>c</sup>	smooth	stable
Debranched 1% OSA waxy maize (47%) <sup>c</sup>	smooth	stable
Debranched 3% quab 342 waxy maize (30%) <sup>c</sup>	smooth	stable
Debranched 3% quab 426 waxy maize (30%) <sup>c</sup>	smooth	stable
$\alpha$ -amylase converted 3% OSA waxy maize	smooth	phase separation
$\alpha$ -amylase converted 1% OSA waxy maize	smooth	phase separation
3% OSA waxy maize	grainy texture	stable
Tapioca dextrin	grainy texture	stable
$\alpha$ -amylase converted waxy maize (pregelatinized)	smooth	phase separation
Corn starch	b	b
Crosslinked, pregelatinized tapioca	b	b
Acid-converted high amylose (50%) corn	b	b
10% quab 342 corn (contains 0.4% Nitrogen)	b	b
Corn dextrin	grainy texture	phase separation
Acid-converted corn	smooth	phase separation

a. OSA is a Octenyl Succinic Anhydride derivative of the starch; Quab 342 is a 3-Chloro-2-Hydroxypropyl-N,N,N-Dimethyldodecyl Ammonium Chloride derivative of the starch; Quab 426 is a 3-Chloro-2-Hydroxypropyl-N,N,N-Dimethyloctadecyl Ammonium Chloride derivative of the starch; and phosphorous oxychloride was used for crosslinking. All starch derivatizations and conversions were by the methods set forth in Example 1.

b. These starches could not be prepared in the suggested formulation at 10% due to the high viscosity of the aqueous phase. The starches were incorporated at 5% and all but the acid-converted high amylose (50%) corn starch could not be prepared. The acid-converted high amylose (50%) corn starch provided a smooth feeling formulation which phase separated after two weeks at 49°C (120°F).

c. Percent short chain amylose.

Only the pullulanas debranched starches produced stable formulations with desirable features. After two months, debranched starch-containing formulations showed no signs of instability, i.e., perspiration like droplets or liquid separation, indicating phase separation. Also, no signs of cracking or discoloration occurred.

Thus, the utility of starch in water-in-oil stick cosmetic compositions was limited to the debranched starches herein. Other modified and unmodified starches were not acceptable in these cosmetics.

#### EXAMPLE 6

This example illustrates the preparation of various skin lotions using enzymatically debranched starch. Skin lotions were prepared according to the following formulations and procedures.

HAND AND BODY LOTION FORMULATION	
Ingredients	Percent by Weight
<b>Phase A</b>	
Cetyl Alcohol	1.00
20 mole Ethoxy Stearyl Alcohol	1.00
Glyceryl Stearate SE	1.00
C <sub>12</sub> - C <sub>15</sub> Alcohols Benzoate	3.00
Octyl Palmitate	3.00
Stearic Acid	2.00
Dimethicone Copolyol	1.00
<b>Phase B</b>	
Deionized Water	69.00
Propylene Glycol	3.00
Fully Debranched Potato Starch <sup>a</sup>	2.00
Carbomer 941 (2% Solution)	12.00
Triethanolamine (99%)	1.00
<b>Phase C</b>	
Preservative <sup>b</sup>	1.00
	100.00

a. Starch contained 89.2% short chain amylose and was prepared by the method of Example 1.

b. A mixture of propylene glycol, diazolidinyl urea, methylparaben and propylparaben.

The ingredients in Phase B were mixed and heated to 80 °C. The ingredients in phase A were mixed, heated to 80 °C and added to Phase B. The formulation was mixed for 15 minutes at 80 °C, allowed to cool to 35 °C and Phase C was added. The formulation was cooled to room temperature and packaged.

The formulation was very white, creamy and viscous but difficult to rub into the skin (i.e., a large amount of drag on the skin). The formulation was unacceptable as a hand lotion. The formulation had tactile properties typical of a night cream.

CATIONIC SKIN MOISTURIZER FORMULATION (MULTI-PROTECTION)	
Ingredients	Percent by Weight
<b>Phase A</b>	
Cetyl Alcohol	2.00
Mineral oil	3.00
Petrolatum	1.00
Tridecyl Neopentanoate	2.50
Dimethicone Copolyol	1.00
Glyceryl Stearate and Laureth-23	1.00
Dimethicone	0.20
Tocopheryl Acetate	0.20
Steareth-21	1.00
<b>Phase B</b>	
Deionized Water	70.90
Stearamidopropyl PG-Dimonium Chloride Phosphate (Monaquat)	2.00
Allantoin	0.50
Aloe Vera Gel (1:1)	5.00
Polyquaternium-10 (Celquat® SC-240)	0.50
Propylene Glycol	4.00
Debranched 1% OSA waxy maize starch <sup>a</sup>	4.00
<b>Phase C</b>	
Preservative <sup>b</sup>	1.00
<b>Phase D</b>	
Fragrance Q4698	0.20
	100.00

a. Debranched by the method of Example 1 to 74.7% short chain amylose.

b. A mixture of propylene glycol, diazolidinyl urea, methylparaben and propylparaben.

The water, monaquat and allantoin were heated to 50°C. Celquat SC-240 was dispersed thoroughly in the water and heated to 80°C. The propylene glycol and starch were slurried and added to the water phase. Phase B was mixed and heated to 80°C, Phase A was added to Phase B at 80°C, and mixed for 15 minutes at 80°C, cooled to 35°C and Phase C and Phase D were added. The formulation was cooled to room temperature and packaged.

The formulation initially left a wet feeling on the skin but dried to a silky residue. The formulation was white and creamy and acceptable when used on the skin.

EMOLLIENT LOTION FORMULATION	
Ingredients	Percent by Weight
<b>Phase A</b>	
Cetyl Alcohol	1.00
Ceteth-20	1.00
Glyceryl Stearate SE	1.00
C <sub>12-15</sub> Alcohols Benzoate	5.00
Octyl Palmitate	5.00
Stearic Acid T.P.	2.00
Dimethicone Copolyol	1.00
<b>Phase B</b>	
Deionized water	77.31
Carbomer 941	0.24
Triethanolamine (99%)	1.00
Propylene Glycol	3.00
Debranched waxy maize starch <sup>a</sup>	2.00
Methylparaben	0.15
Propylparaben	0.10
<b>Phase C</b>	
Diazolidinyl Urea	0.20
	<u>100.00</u>

a. Debranched by the method of Example 1 to 12.2% short chain amylose.

The carbopol was dispersed into the water and heated to 80 °C. The remaining Phase B ingredients were added and mixed thoroughly. Phase A was mixed, heated to 80 °C and added to Phase B. The formulation was mixed for 15 minutes at 80 °C, cooled to 40 °C and Phase C was added. The formulation was cooled to room temperature and packaged.

The formulation was non-greasy, non-tacky and acceptable when used on the skin.

#### **EXAMPLE 7**

This example illustrates the preparation of various emulsion-containing cosmetic compositions using enzymatically debranched starch.

Cosmetic compositions are prepared according to the following formulations and procedures.



NON-GREASY LOTION FORMULATION	
Ingredient	Percent by Weight
<b>Phase A</b>	
Cetyl Alcohol	1.00
Glyceryl Stearate	1.00
Ceteth-20	1.00
Octyl Palmitate	3.00
Dimethicone Copolyol	1.00
Stearic Acid T.P.	3.00
<b>Phase B</b>	
Deionized Water	86.35
Carbomer 941	0.20
Triethanolamine (99%)	1.00
Debranched Waxy Maize Starch <sup>a</sup>	2.00
Methylparaben	0.15
Propylparaben	0.10
<b>Phase C</b>	
Diazolidinyl Urea	0.20
	100.00

a. Debranched by the method of Example 1 to 78% short chain amylose.

Preparation of the non-greasy lotion is by the method set forth in Example 6 for the emollient lotion.

DRY SKIN LOTION FORMULATION	
Ingredients	Percent by Weight
<b>Phase A</b>	
Cetyl Alcohol	1.00
Ceteth-21	1.00
Glyceryl Stearate SE	1.00
Tridecyl Neopentanoate	5.00
Octyl Palmitate	3.00
Stearic Acid T.P.	2.00
Dimethicone	0.50
<b>Phase B</b>	
Deionized Water	79.80
Carbomer 941	0.25
Triethanolamine (99%)	1.00
Propylene Glycol	3.00
Debranched waxy maize starch <sup>a</sup>	2.00
Methylparaben	0.15
Propylparaben	0.10
<b>Phase C</b>	
Diazolidinyl urea	0.20
	100.00

a. Debranched by the method of Example 1 to 78% short chain amylose.

The dry skin lotion is prepared by the same method as the non-greasy lotion.

BABY LOTION FORMULATION	
Ingredients	Percent by Weight
<b>Phase A</b>	
C <sub>12-15</sub> Alcohols Benzoate	10.00
Stearic Acid T.P.	2.50
Glyceryl Stearate SE	2.00
Ceteth-20	1.00
Tocopheryl Acetate	0.50
Cetyl Alcohol	1.00
Dimethicone Copolyol	1.00
<b>Phase B</b>	
Deionized water	68.15
Carbomer 934	0.20
Triethanolamine (99%)	1.20
Aloe vera gel (1:1)	10.00
Debranched waxy maize starch <sup>a</sup>	2.00
Methylparaben	0.15
Propylparaben	0.10
<b>Phase C</b>	
Imidazolidinyl Urea	0.20
	100.00

a. Debranched by the method of Example 1 to 78% short chain amylose.

The baby lotion is prepared by the same method as the non-greasy lotion.

MOISTURIZER SUNSCREEN FORMULATION (EVERYDAY; S.P.F. 6)	
Ingr d l nts	Percent by Weight
<b>Phase A</b>	
Octyl Salicylate	3.00
Benzophenone-3	2.00
C <sub>12-15</sub> alcohols benzoate	5.00
Stearic Acid T.P.	2.00
Glyceryl Stearate SE	2.00
Tocopheryl Acetate	0.20
Cetyl Alcohol	1.00
PEG-40 Stearate	1.00
Dimethicone Copolyol	1.00
<b>Phase B</b>	
Deionized water	72.00
Carbomer 941	0.15
Triethanolamine (99%)	0.70
Aloe Vera Gel (1:1)	5.00
Glycerin	3.00
Methylparaben	0.15
Propylparaben	0.10
Debranched OSA waxy maize starch <sup>a</sup>	1.50
<b>Phase C</b>	
Diazolidinyl Urea	0.20
	100.00

a. Debranched by the method of Example 1 to 78% short chain amylose and treated with 3% OSA treated.

The moisturizer sunscreen formulation is prepared by the same method as the non-greasy lotion.

FACIAL MASK FORMULATION	
Ingredients	Percent by Weight
<b>Phase A</b>	
Deionized water	87.55
Carbomer 934	0.50
Triethanolamine (99%)	0.50
Polysorbate 80	1.00
Debranched waxy maize starch <sup>a</sup>	10.00
Methylparaben	0.15
Propylparaben	0.10
<b>Phase B</b>	
Diazolidinyl Urea	0.20
	100.00

a. Debranched by the method of Example 1 to 60% short chain amylose.

The facial mask formulation is prepared by the same method as the non-greasy lotion, except that no Phase C is used.

CLEANSING CREAM FORMULATION	
Ingredients	Per cent by Weight
<b>Phase A</b>	
Stearic Acid D.P.	20.00
Mineral Oil	5.00
Cetyl Alcohol	0.50
Octyl Palmitate	5.00
<b>Phase B</b>	
Deionized water	61.05
Propylene Glycol	5.00
Debranched waxy maize starch <sup>a</sup>	2.00
Triethanolamine (99%)	1.00
Methylparaben	0.15
Propylparaben	0.10
<b>Phase C</b>	
Imidazolidinyl Urea	0.20
	100.00

a. Debranched by the method of Example 1 to 31.7% short chain amylose.

The cleansing cream formulation is prepared by the same method as the non-greasy lotion.

OIL-FREE EMOLLIENT LOTION FORMULATION	
Ingredients	Percent by Weight
<b>Phase B</b>	
Debranched waxy maize starch <sup>a</sup>	25.0
Propylene glycol	0.5
Polysorbate 20	1.0
Dimethicone copolyol	2.0
Deionized water	70.0
<b>Phase C</b>	
Preservative <sup>b</sup>	1.5
	100.00

a. Debranched by the method of Example 1 to 78% short chain amylose.

b. A mixture of propylene glycol, diazolidinyl urea, methylparaben and propylparaben.

The oil-free formulation is prepared by the same method as the non-greasy lotion, except that no Phase A is used. The oil-free, emulsion-like lotion is opaque and viscous. It may be used as a carrier or base for pharmacologically active agents.

## Claims

1. An emulsion containing cosmetic composition, wherein the emulsion comprises an aqueous dispersion of 15 to 40%, by weight, of an enzymatically degraded starch, which starch has been debranched by treatment with an  $\alpha$ -1,6-D-glucanohydrolase to yield up to 100%, by weight, linear polymers containing from 15 to 65 anhydroglucose units linked by  $\alpha$ -1,4-D-glucosidic bonds (short chain amylose).

2. The emulsion of Claim 1, further comprising long chain amylose, amylopectin, or partially debranched amylopectin, or a combination thereof.
- 5 3. The emulsion of Claim 1, wherein the starch is further modified by derivatization, conversion, or crosslinking, or a combination thereof.
4. The emulsion of Claim 1, wherein the starch is selected from waxy maize starch, corn starch, high amylose corn starch, tapioca starch, potato starch, wheat starch, rice starch and waxy rice starch, and combinations thereof.
- 10 5. The emulsion of Claim 1, wherein the alpha-1,6-D-glucoanhydrolase is selected from pullulanase and isoamylase.
6. The emulsion containing cosmetic composition of Claim 1, wherein the composition is selected from skin lotions, creams, cosmetic sticks, roll-on moisturizers, roll-on deodorants, stick deodorants, lipsticks, lip balms, facial cleaners, cosmetic soaps, and sunscreens.
- 15 7. A emulsion-containing cosmetic stick composition, comprising 1 to 16% starch which has been enzymatically debranched to yield from 15 to 100%, by weight, linear polymers containing from 15 to 65 anhydroglucose units linked by alpha-1,4-D-glucosidic bonds (short chain amylose); 2 to 35%, by weight, water; 35 to 90%, by weight, hydrophobic base, selected from oil, wax and fat; 5 to 20%, by weight, emulsifier(s); and one or more adjuncts selected from dye(s), preservative(s), fragrance(s), flavor(s), sunscreen agent(s), opacifier(s), and filler(s).
- 20 8. The cosmetic stick composition of claim 7, further comprising long chain amylose, amylopectin, or partially debranched amylopectin, or a combination thereof.
9. The cosmetic stick composition of Claim 7, wherein the starch is further modified by derivatization, conversion, or crosslinking, or a combination thereof.
- 30 10. The cosmetic stick composition of Claim 7, wherein the starch is selected from waxy maize starch, corn starch, high amylose corn starch, tapioca starch, potato starch, wheat starch, rice starch and waxy rice starch, and combinations thereof.
- 35 11. The cosmetic composition of Claim 7, wherein the starch is enzymatically debranched by treatment with an alpha-1,6-D-glucoanhydrolase selected from pullulanase and isoamylase.
12. The cosmetic stick composition of Claim 7, wherein the composition is selected from stick moisturizers, stick deodorants, lipsticks, lip balms, moisturizing soaps, and stick sunscreens.
- 40 13. A method for formulating a cosmetic stick composition which comprises:
  - a) dispersing a starch which has been debranched by alpha-1,6-D-glucanohydrolase in an aqueous solvent at 15 to 40%, by weight, solids;
  - b) heating the dispersed starch to 70-100°C;
  - 45 c) adding to the dispersed starch a hydrophobic phase at 70-100°C, which hydrophobic phase comprises at least one hydrophobic ingredient and at least one emulsifier;
  - d) blending the dispersed starch into the hydrophobic phase to provide an emulsion; and
  - e) forming the cosmetic stick from the emulsion; whereby the emulsion is uniform and the cosmetic stick composition is stable.
- 50 14. The method of Claim 13, wherein the enzymatically debranched starch comprises up to 100%, by weight, short chain amylose.
15. The method of Claim 14, wherein the enzymatically debranched starch further comprises long chain amylose, amylopectin, or partially debranched amylopectin, or a combination thereof.
- 55 16. The method of Claim 14, wherein the starch is further modified by derivatization, conversion, or crosslinking, or a combination thereof.

17. The method of Claim 13, wherein the enzymatically debranched starch is selected from waxy maize starch, corn starch, high amylose corn starch, tapioca starch, potato starch, wheat starch, rice starch and waxy rice starch, and combinations thereof.
- 5 18. The method of Claim 13, wherein the enzymatically debranched starch is prepared with an alpha-1,6-D-glucanohydrolase selected from pullulanase and isoamylase.
19. The method of Claim 13, wherein the cosmetic stick composition is selected from stick moisturizers, stick deodorants, lipsticks, lip balms, moisturizing soaps, and stick sunscreens.
- 10 20. The use of a composition comprising an aqueous dispersion of 15 to 40 %, by weight, of an enzymatically degraded starch, which starch has been debranched by treatment with an alpha-1,6-D-glucanohydrolase to yield up to 100 %, by weight, short chain amylose within an oil-free cosmetic composition.
- 15 21. An oil-free cosmetic composition, wherein the composition comprises an aqueous dispersion of 15 to 40 %, by weight, of an enzymatically degraded starch, which starch has been debranched by treatment with an alpha-1,6-D-glucanohydrolase to yield up to 100 %, by weight, linear polymers containing from 15 to 65 anhydroglucose units linked by alpha-1,4-D-glucosidic bonds (short chain amylose), and further comprises 0,5 to 15 %, by weight, emulsifier(s); 0,5 to 5 %, by weight, preservative(s); and one or more adjuncts selected from dye(s); fragrance(s); flavor(s); sunscreen agent(s); filler(s); and pharmacologically active agent(s).
- 20 22. The emulsion of claim 1, wherein the starch is waxy maize starch, waxy rice starch, or barley starch.
- 25 23. The emulsion of claim 1, wherein the starch is a converted, debranched waxy starch, preferably 50 WF acid-converted waxy maize or waxy rice starch.
24. The emulsion of claim 1, wherein the starch is OSA waxy maize starch.

#### 30 Patentansprüche

1. Emulsionshaltige kosmetische Zusammensetzung, in der die Emulsion eine wäßrige Dispersion von 15 bis 40 Gew.-% einer enzymatisch abgebauten Stärke umfaßt, die durch Behandlung mit einer alpha-1,6-D-Glucanohydrolase entzweigt worden ist, wobei bis zu 100 Gew.-% lineare Polymere mit etwa 15 bis 65 Anhydroglucoseeinheiten, die durch alpha-1,4-D-Glucosidbindungen verbunden sind, (kurzkettige Amylose) erhalten worden ist.
- 35 2. Emulsion nach Anspruch 1, die ferner langkettige Amylose, Amylopektin oder partiell entzweigtes Amylopektin oder eine Kombination davon umfaßt.
- 40 3. Emulsion nach Anspruch 1, in der die Stärke durch Derivatisierung, Umwandlung oder Vernetzung oder eine Kombination davon weiter modifiziert ist.
- 45 4. Emulsion nach Anspruch 1, in der die Stärke aus Wachsmaisstärke, Maisstärke, Hochamylosemaisstärke, Tapiokastärke, Kartoffelstärke, Weizenstärke, Reisstärke und Wachstreisstärke und Kombinationen davon ausgewählt ist.
- 50 5. Emulsion nach Anspruch 1, in der die alpha-1,6-D-Glucanohydrolase aus Pullulanase und Isoamylase ausgewählt ist.
- 55 6. Emulsionshaltige kosmetische Zusammensetzung nach Anspruch 1, in der die Zusammensetzung aus Hautlotionen, Cremes, kosmetischen Stiften, Roll-on-Moisturizern, Roll-on-Deodorantien, Stiftdeodorantien, Lippenstiften, Lippenbalsamprodukten, Gesichtereinigern, kosmetischen Seifen und Sonnenschutzmitteln ausgewählt ist.
7. Emulsionshaltige kosmetische stiftzusammensetzung, umfassend: 1 bis 16 % Stärke, die enzymatisch entzweigt worden ist, wobei 15 bis 100 Gew.-% lineare Polymere mit 15 bis 65 Anhydroglucoseeinheiten

- ten, die durch alpha-1,4-D-Glucosidbindungen verbunden sind, (kurzkettige Amylose) erhalten worden sind; 2 bis 35 Gew.-% Wasser; 35 bis 90 Gew.-% hydrophobe Grundlange ausgewählt aus Öl, Wachs und Fett; 5 bis 20 Gew.-% Emulgator(en); und ein oder mehrere Hilfsmittel, ausgewählt aus Farbstoff(en), Konservierungsmittel(n), Duftstoff(en), Aromastoff(en), Sonnenschutzmittel(n), Opazifizierungsmittel(n) und Füllstoff(en).
8. Kosmetische Stiftzusammensetzung nach Anspruch 7, die ferner langkettige Amylose, Amylopektin oder partiell entzweigtes Amylopektin oder eine Kombination davon umfaßt.
  9. Kosmetische Stiftzusammensetzung nach Anspruch 7, in der die Stärke durch Derivatisierung, Umwandlung oder Vernetzung oder eine Kombination davon weiter modifiziert ist.
  10. Kosmetische Stiftzusammensetzung nach Anspruch 7, in der die Stärke aus Wachsmaisstärke, Maisstärke, Hochamylosemaisstärke, Tapiokastärke, Kartoffelstärke, Weizenstärke, Reisstärke und Wachsisstärke und Kombinationen davon ausgewählt ist.
  11. Kosmetische Zusammensetzung nach Anspruch 7, in der die Stärke durch Behandlung mit einer alpha-1,6-D-Glucanohydrolase, ausgewählt aus Pullulanase und Isoamylase, enzymatisch entzweig ist.
  12. Kosmetische Stiftzusammensetzung nach Anspruch 7, in der die Zusammensetzung aus Stiftmoisturizern, Stiftdeodorantien, Lippenstiften, Lippenbalsamprodukten, Feuchtigkeitsseifen und Stiftsonnenschutzmitteln ausgewählt ist.
  13. Verfahren zum Formulieren einer kosmetischen Stiftzusammensetzung, das umfaßt:
    - a) Dispergieren einer Stärke, die durch alpha-1,6-D-Glucanohydrolase entzweig worden ist, in einem wäßrigen Lösungsmittel bei 15 bis 40 Gew.-% Feststoffen;
    - b) Erhitzen der dispergierten Stärke auf 70 bis 100 °C;
    - c) bei 70 bis 100 °C Zugabe einer hydrophoben Phase zur dispergierten Stärke, wobei die hydrophobe Phase mindestens einen hydrophoben Bestandteil und mindestens einen Emulgator umfaßt;
    - d) Einmischen der dispergierten Stärke in die hydrophobe Phase zur Ausbildung einer Emulsion
    - e) Bilden des kosmetischen Stiftes aus der Emulsion, wobei die Emulsion einheitlich ist und die kosmetische Stiftzusammensetzung stabil ist.
  14. Verfahren nach Anspruch 13, in welchem die enzymatisch entzweigte Stärke bis zu 100 Gew.-% kurzkettige Amylose umfaßt.
  15. Verfahren nach Anspruch 14, in welchem die enzymatisch entzweigte Stärke ferner langkettige Amylose, Amylopektin oder partiell entzweigtes Amylopektin oder eine Kombination davon umfaßt.
  16. Verfahren nach Anspruch 14, in welchem die Stärke durch Derivatisierung, Umwandlung oder Vernetzung oder eine Kombination davon weiter modifiziert ist.
  17. Verfahren nach Anspruch 13, in welchem die enzymatisch entzweigte Stärke aus Wachsmaisstärke, Maisstärke, Hochamylosemaisstärke, Tapiokastärke, Kartoffelstärke, Weizenstärke, Reisstärke und Wachsisstärke und Kombinationen davon ausgewählt ist.
  18. Verfahren nach Anspruch 13, in welchem die enzymatisch entzweigte Stärke mit einer alpha-1,6-D-Glucanohydrolase, ausgewählt aus Pullulanase und Isoamylase, hergestellt ist.
  19. Verfahren nach Anspruch 13, in welchem die kosmetische Stiftzusammensetzung aus Stiftmoisturizern, Stiftdeodorantien, Lippenstiften, Lippenbalsamprodukten, befeuchtenden Seifen und Stiftsonnenschutzmitteln ausgewählt ist.
  20. Verwendung einer Zusammensetzung, die eine wäßrige Dispersion von 15 bis 40 Gew.-% einer enzymatisch entzweigten Stärke umfaßt, die durch Behandlung mit einer alpha-1,6-D-Glucanohydrolase entzweig worden ist, wobei bis zu 100 Gew.-% kurzkettige Amylose erhalten worden sind, in einer ölfreien kosmetischen Zusammensetzung.

21. Ölfreie kosmetische Zusammensetzung, in der die Zusammensetzung eine wäßrige Dispersion von 15 bis 40 Gew.-% einer enzymatisch entzweigten Stärke umfaßt, die durch Behandlung mit einer alpha-1,6-D-Glucanohydrolase entzweigt worden ist, wobei bis zu 100 Gew.-% lineare Polymere mit 15 bis 65 Anhydroglucoseeinheiten, die durch alpha-1,4-D-Glucosidbindungen verbunden sind, (kurzkettige Amylose) erhalten worden sind, und die ferner 0,5 bis 15 Gew.-% Emulgator(en), 0,5 bis 5 Gew.-% eines oder mehrerer Konservierungsmittel und ein oder mehrere Hilfsmittel, ausgewählt aus Farbstoff(en), Duftstoff(en), Aromastoff(en), Sonnenschutzmittel(n), Füllstoff(en) und pharmakologisch aktiven Mittel(n), umfaßt.
22. Emulsion nach Anspruch 1, in der die Stärke Wachsmaisstärke, Wachsreisstärke oder Gerstenstärke ist.
23. Emulsion nach Anspruch 1, in der die Stärke eine umgewandelte entzweigte Wachsstärke, vorzugsweise 50 WF säureumgewandelte Wachsmais- oder Wachsreisstärke, ist.
24. Emulsion nach Anspruch 1, in der die Stärke OSA-Wachsmaisstärke ist.

### Revendications

1. Composition de cosmétique contenant une émulsion, dans laquelle l'émulsion comprend une dispersion aqueuse de 15 à 40 %, en poids, d'un amidon ayant subi une dégradation enzymatique, amidon qui a été soumis à une déramification par traitement avec une alpha-1,6-D-glucanohydrolase pour obtenir jusqu'à 100 %, en poids, de polymères linéaires contenant 15 à 65 motifs anhydroglucose liés par des liaisons alpha-1,4-D-glucosidiques (amylose à chaîne courte).
2. Emulsion suivant la revendication 1, comprenant en outre de l'amylose à chaîne longue, de l'amylopectine ou de l'amylopectine partiellement déramifiée, ou bien une de leurs associations.
3. Emulsion suivant la revendication 1, dans laquelle l'amidon a été soumis à une modification supplémentaire par transformation en dérivé, hydrolyse ou réticulation ou bien une association de ces modes opératoires.
4. Emulsion suivant la revendication 1, dans laquelle l'amidon est choisi entre l'amidon de maïs cireux, l'amidon de maïs, l'amidon de maïs à haute teneur en amylose, la fécule de manioc, la fécule de pomme de terre, l'amidon de blé, l'amidon de riz et l'amidon de maïs cireux ainsi que leurs associations.
5. Emulsion suivant la revendication 1, dans laquelle l'alpha-1,6-D-glucanohydrolase est choisie entre la pullulanase et l'isoamylase.
6. Composition de cosmétique en émulsion suivant la revendication 1, qui est choisie entre des lotions pour la peau, des crèmes, des cosmétiques en bâtonnets, des formulations hydratantes en flacons à bille, des déodorants en flacons à bille, des déodorants en bâtonnets, des rouges à lèvres, des baumes pour les lèvres, des démaquillants, des savons cosmétiques et des écrans solaires.
7. Composition cosmétique en émulsion présentée en bâtonnet, comprenant 1 à 16 % d'un amidon qui a été soumis à une déramification enzymatique donnant 15 à 100 %, en poids, de polymères linéaires contenant 15 à 65 % de motifs anhydroglucose liés par des liaisons alpha-1,4-D-glucosidiques (amylose à chaîne courte), 2 à 35 %, en poids, d'eau ; 35 à 90 %, en poids, d'une base hydrophobe choisie entre une huile, une cire et une matière grasse ; 5 à 20 %, en poids, d'un ou plusieurs émulsifiants ; et un ou plusieurs agents auxiliaires choisis entre un ou plusieurs colorants, un ou plusieurs conservateurs, un ou plusieurs parfums, un ou plusieurs arômes, un ou plusieurs agents à effet d'écran solaire, un ou plusieurs opacifiants et une ou plusieurs charges.
8. Composition de cosmétique en bâtonnet suivant la revendication 7, comprenant en outre de l'amylose à chaîne longue, de l'amylopectine ou de l'amylopectine partiellement déramifiée, ou bien une de leurs associations.



9. Composition de cosmétique en bâtonnet suivant la revendication 7, dans laquelle l'amidon a été soumis à une modification supplémentaire par transformation en un dérivé, hydrolyse ou réticulation, ou bien une association de ces modes opératoires.
- 5 10. Composition de cosmétique en bâtonnet suivant la revendication 7, dans laquelle l'amidon est choisi entre l'amidon de maïs cireux, l'amidon de maïs, l'amidon de maïs à haute teneur en amylose, la fécule de manioc, la fécule de pomme de terre, l'amidon de blé, l'amidon de riz et l'amidon de riz cireux ainsi que leurs associations.
- 10 11. Composition de cosmétique suivant la revendication 7, dans laquelle l'amidon a été soumis à une déramification enzymatique par traitement avec une alpha-1,6-D-glucanohydrolase choisie entre la pullulanase et l'isoamylase.
12. Composition de cosmétique en bâtonnet suivant la revendication 7, qui est choisie entre des formu-  
15 lations hydratantes en bâtonnets, des déodorants en bâtonnets, des rouges à lèvres, des baumes pour les lèvres, des savons hydratants et des écrans solaires en bâtonnets.
13. Procédé pour formuler une composition de cosmétique en bâtonnet, qui comprend :  
20 a) la dispersion d'un amidon qui a été soumis à une déramification par une alpha-1,6-D-glucanohydrolase dans un solvant aqueux à une teneur en matières solides de 15 à 40 % en poids ;  
b) le chauffage de l'amidon dispersé à une température de 70 à 100 °C ;  
c) l'addition à l'amidon dispersé d'une base hydrophobe à une température de 70 à 100 °C, base hydrophobe qui comprend au moins un ingrédient hydrophobe et au moins un émulsionnant ;  
25 d) le mélange de l'amidon dispersé dans la phase hydrophobe pour former une émulsion ; et  
e) la formation du bâtonnet de cosmétique à partir de l'émulsion ; l'émulsion obtenue étant ainsi uniforme et la composition de cosmétique en bâtonnet étant ainsi stable.
14. Procédé suivant la revendication 13, dans lequel l'amidon ayant subi une déramification enzymatique comprend jusqu'à 100 %, en poids, d'amylose à chaîne courte.
- 30 15. Procédé suivant la revendication 14, dans lequel l'amidon ayant subi une déramification enzymatique comprend en outre de l'amylose à chaîne longue, de l'amylopectine ou de l'amylopectine partiellement déramifiée, ou bien une de leurs associations.
- 35 16. Procédé suivant la revendication 14, dans lequel l'amidon a été soumis à une modification supplémentaire par transformation en dérivé, hydrolyse ou réticulation, ou bien une de leurs associations.
17. Procédé suivant la revendication 13, dans lequel l'amidon ayant subi une déramification enzymatique est choisi entre l'amidon de maïs cireux, l'amidon de maïs, l'amidon de maïs à haute teneur en  
40 amylose, la fécule de manioc, la fécule de pomme de terre, l'amidon de blé, l'amidon de riz et l'amidon de maïs cireux ainsi que leurs associations.
18. Procédé suivant la revendication 13, dans lequel l'amidon ayant subi une déramification enzymatique est préparé avec une alpha-1,6-D-glucanohydrolase choisie entre la pullulanase et l'isoamylase.
- 45 19. Procédé suivant la revendication 13, dans lequel la composition de cosmétique en bâtonnet est choisie entre des formulations hydratantes en bâtonnets, des déodorants en bâtonnets, des rouges à lèvres, des baumes pour les lèvres, des savons hydratants et des écrans solaires en bâtonnets.
- 50 20. Utilisation d'une composition comprenant une dispersion aqueuse de 15 à 40 %, en poids, d'un amidon ayant subi une dégradation enzymatique, amidon qui a été soumis à une déramification par traitement avec une alpha-1,6-D-glucanohydrolase donnant jusqu'à 100 %, en poids, d'amylose à chaîne courte, dans une composition de cosmétique sans huile.
- 55 21. Composition de cosmétique sans huile, qui comprend une dispersion aqueuse de 15 à 40 %, en poids, d'un amidon ayant subi une dégradation enzymatique, amidon qui a été soumis à une déramification par traitement avec une alpha-1,6-D-glucanohydrolase donnant jusqu'à 100 %, en poids, de polymères linéaires contenant 15 à 65 motifs anhydroglucose liés par des liaisons alpha-1,4-D-glucosidiques

(amylose à chaîne courte), et qui comprend en outre 0,5 à 15 %, en poids, d'un ou plusieurs émulsifiants ; 0,5 à 5 %, en poids, d'un ou plusieurs conservateurs ; et un ou plusieurs agents auxiliaires choisis entre un ou plusieurs colorants, un ou plusieurs parfums, un ou plusieurs arômes, un ou plusieurs écrans solaires, une ou plusieurs charges et un ou plusieurs agents pharmacologiquement actifs.

22. Emulsion suivant la revendication 1, dans laquelle l'amidon est l'amidon de maïs cireux, l'amidon de riz cireux ou l'amidon d'orge.

23. Emulsion suivant la revendication 1, dans laquelle l'amidon est un amidon cireux hydrolysé déramifié, de préférence un amidon de maïs cireux ou de riz cireux ayant subi une hydrolyse avec un acide jusqu'à une valeur de fluidité en milieu aqueux de 50.

24. Emulsion suivant la revendication 1, dans laquelle l'amidon est l'amidon de maïs cireux OSA.